



Liquid Eyeliner - Fabulous Green-gold

 COLOUR COSMETICS | EYE MAKE UP
 RR-03-01-01

WorléeMicromer C50/25 is free of preservatives and emulsifying agents. WorléeMicromer C50/25 builds clear, glossy films and improves dispersion of pigments in the formulation.

Phase	Ingredient	INCI	Supplier	%
A	Water	Aqua		57,45
	Keltrol CG-T	Xanthan Gum	CP Kelco	0,30
	Veegum HV	Magnesium Aluminium Silicate	RTVanderbilt	0,50
	1,2-Propylene Glycol	Propylene Glycol	Sigma-Aldrich	3,00
	Organic Glycerin	Glycerin	Worlée	3,00
B	Palmac 98-18	Stearic Acid	Berg + Schmidt	2,00
	Imwitor 900	Glyceryl Stearate	Cremer Care	1,00
	Rofanol 90/95 V	Oleylalcohol	Ecogreen / DHW	1,00
C	SynCrystal Gold	Synthetic Fluorphlogopite and Titanium Dioxide	Eckart	5,00
	Colorona Egyptian Emerald	Titanium Dioxide and Iron Oxide and Mica and Chromium Oxide Green	Merck	5,00
D	WorléeMicromer C50/25	Ammonium Acrylates Copolymer	Worlée	16,00
	Xiameter PMX-1184 Silicone Fluid	Dimethicone and Trisiloxane	Dow Corning	5,00
	Euxyl PE 9010	Phenoxyethanol and Ethylhexylglycerin	Schülke & Mayr	0,75
Total:				100,00

PROCEDURE

1. Add Propylene Glycol and Glycerin into water and mix until uniform.
2. Heat up to 75°C and then disperse Xanthan Gum and Magnesium Aluminium Silicate into water phase. Heat Phase B to 75°C. Emulsify phase B into phase A. Homogenize for 2 min. to form an emulsion.
3. While stirring add phase C.
4. Cool down to room temperature and add phase D.
5. Stir until uniform.

PARAMETER

None

STABILITY

Stable for at least 3 months at RT and 40°C.

CREATED AT: 2013-10-21

BY: SAM